

## AIR ENTRAINING CONCRETE ADMIXTURE

### DESCRIPTION

Conair is a liquid air entraining agent for use in concrete and mortar mixes. It is used to improve the workability, cohesion, and durability of concrete and mortar by the entrainment of minute air bubbles of controlled size and spacing, uniformly distributed throughout the mix. Conair complies with ASTM C260-81 for air entraining admixtures. It provides freeze thaw protection in cold climates.

### USES & ADVANTAGES

Conair is used to produce workable and durable concrete for dams and reservoirs, tunnels, mass concrete structures, roads, runways, taxiways etc.

Advantages include:-

- Improves permeability
- Improves workability.
- Improves durability.
- Cohesion of mixes is improved and bleeding reduced.
- Volume yield of concrete or mortar is increased.
- Harsh mixes are improved.
- Easy to use.
- Ready to use.
- Freeze thaw protection.

### PROPERTIES

Appearance:	Light brown liquid
Specific Gravity:	Approx. 1.0 kg/l
Shelf Life:	1 year when unopened
Storage:	Free from frost in shade. Reseal after use.
pH Value:	8-10

### DISPENSING / APPLICATION

Conair is added directly to the mixing water prior to its addition to the aggregates. Conair can be used with other admixtures providing these are added separately to the mix. Do not premix.

### IMPORTANT NOTES

Overdosing will result in a high air content with resulting reductions in strength. To ensure consistent results air contents should be regularly monitored particularly if other materials are subject to variation.

### DOSAGE

The dosage of Conair normally is in the range of 0.03 - 0.2 litre per 100 kg of total cementitious material, however,

there is no standard dosage. The dosage level is not predictable because of varying materials and concrete mix designs.

Factors influencing air entrainment are: cement quality, sand grading, sand to aggregate ratio, slump, temperatures, cement replacements or pozzolanic materials such as PFA, GGBFS or silica fume.

Trial mixes may be started at 0.1% by weight of cement and the dosage adjusted depending on the results obtained under actual job conditions.

Mixes containing other plasticisers/retarders may require less air entrainer than plain mixes. Vary the dosage until the desired effect is achieved.

### PACKAGING

25 litre plastic pails and 200 litre drums.

### STORAGE & SHELF LIFE

Shelf life up to 9 months if stored in original unopened package in shaded conditions.

### HEALTH & SAFETY

As with all chemical products care should be taken during use and storage to avoid contact with skin eyes and mouth. If accidentally ingested immediately seek prompt medical attention, do not induce vomiting and give copious amounts of water to drink.

### TECHNICAL SERVICE

The Cormix International Technical Service Department is available to assist you in the correct use of our products and its resources are at your disposal entirely without obligation.

### QUALITY ASSURANCE

ISO 9001 : 2008 verified by TUV Nord.

### CONTACT DETAILS

Cormix International Limited

Regional Office,

89 Romkloa Road, Sansab, Minburi, Bangkok 10510

Tel. (66 2) 917 3955-8, 543 8890

Fax. (66 2) 917 3959, 543 8891

<http://www.cormix.com> E-mail : [info@cormix.com](mailto:info@cormix.com)

Rev. 011 : Jun 2012

NOTE : Every reasonable precaution is taken in the manufacture of all CORMIX-products to ensure that they comply with CORMIX's high standard of quality. The recommendations and properties of the product are based upon what is believed to be the most reliable information available, and are not intended as recommendations which infringe on other patents. Although all CORMIX-products are subject to rigid quality tests, no specific guarantee can be given, because results depend, not only on quality, but also on other factors beyond our control. We welcome therefore consultation in the event of doubt concerning application, or performance, and point out that oral recommendations, which vary from the instructions contained herein, are not binding without written confirmation by CORMIX. All transactions shall be subject to our terms and conditions of sale-delivery-and-service. This data sheet supercedes the previous one and a reprint may be issued without notice to supercede this edition, as and when deemed necessary. The information given in this leaflet is to the best of our knowledge true and reliable. Field service where provided does not constitute supervisory responsibility. Our guarantee is therefore limited to the quality of materials delivered.