

PLASTICISED EXPANDING GROUT ADMIXTURE

DESCRIPTION

Congrout Admix is a powdered admixture for use in cementitious grouts and concrete. It is formulated to produce improved grout quality and increased durability, while overcoming problems of settlement and plastic shrinkage using a gaseous expansion mechanism.

USES & ADVANTAGES

Congrout Admix should be used as a grout admixture for all cementitious mixes where restrained expansion is required. Typical uses are under plate and bed grouting, space grouting, anchor bolt and duct grouting.

Advantages include:-

- Provides positive gaseous expansion to counteract shrinkage in cementitious grouts.
- High flow grout mixes obtained using **Congrout Admix** are easier to pump or place.
- Low water/cement ratio obtainable with **Congrout Admix** reduces permeability, improves strength and durability.
- Produces cementitious grouts with excellent non-corrosive bonding and maximum bearing capacity.
- **Congrout Admix** contains no iron, chlorides or other deleterious materials.

PROPERTIES

Appearance:	Grey powder
Apparent Density:	Approx. 0.7 kg. /l.
Chloride Content:	Nil

MIXING

The required quantities of sand, cement and **Congrout Admix** are batched together and mixed into the correct volume of water, using a mechanically powered mixer. Small quantities can be mixed using a slow speed electric drill fitted with a high shear paddle. Larger quantities require a purpose-designed grout mixer to achieve thorough mixing. Mix continuously for 5 minutes to ensure that a smooth homogeneous grout is obtained. It is important that sufficient materials, equipment and personnel are available to enable the grouting operation to be carried out continuously. Storage or holding facilities for the grout may be useful, however, they should be fitted with some means of agitation to maintain fluidity.

APPLICATION

Areas to be grouted require thorough preparation in the conventional manner, to provide a clean, sound, substrate free from defects or contamination. Pre-wet the surfaces

to be grouted preferably 24 hours before grouting, removing excess free water and then grout. The grout should be poured, pumped, injected or trowelled into place within 30 minutes of mixing, to achieve optimum expansion characteristics.

Addition Rate:

Neat cement grouts	250 g. Congrout Admix per 50 kg. cement equivalent to 0.5% by weight of cement.
1 : 1 Cement : sand grouts	250 g. Congrout Admix per 50 kg. cement equivalent to 0.5% by weight of cement.
Grouts having : Cement Ratio of 2 : 1 or higher	500 g. Congrout Admix Sand per 50 kg. cement equivalent to 1.0% by weight of cement.

Yield:

OPC	0.5 mm Sand	Water	Congrout Admix	Approx. Yield
50 kg.	Nil	22 litre	250 gram	36 litre
50 kg.	50 kg.	24 litre	250 gram	57 litre
50 kg.	100 kg.	26 litre	500 gram	80 litre

Water Content:

The plasticising action of **Congrout Admix** enables high flow grout mixes to be produced, using low water/cement ratios. Alternatively, water contents can be reduced while maintaining workability - a water reduction of 10% - 15% is typical.

Loss of Flow:

Cementitious grout mixes containing **Congrout Admix** have slightly extended placement times without detriment to strength development.

Expansion:

Unrestrained expansion is typically between 1-4%. The controlled positive expansion in wet grout overcomes plastic settle according to ASTM C-827. Expansion takes place between 15 minutes & 2 hours after mixing.

CURING

Good curing is essential on all exposed surfaces particularly in dry, sunny conditions. Failure to do so will reduce strength and durability. Immediately after completion, apply two coats of **Corcure 90** curing/membrane to all exposed surfaces. Alternative methods are water ponding, mist spraying and the like, but in all cases these must be maintained for at least 7 days. Keep the grout above 8°C at all times during application and cure.

PLASTICISED EXPANDING GROUT ADMIXTURE

OVERDOSING

Slight overdosing will increase both workability and volume of gas liberated. Serious overdosing (2 - 3 times recommended values) causes retardation of set and strength development and frothing of the mix. In addition there is a major increase in expansion.

IMPORTANT NOTES

Congrout Admix's performance may be influenced by mixing procedures, cement properties adding of water and temperatures. Therefore tests on site should be undertaken.

Congrout Admix should not be used with cement containing Fly Ash.

DOSAGES

0.5 - 2% by weight of cement.

PACKAGING

Congrout Admix is supplied in 0.5 kg. packs or 15 kg. bags.

STORAGE & SHELF LIFE

Store in dry shaded conditions. The shelf life is at least 12 months if kept dry in original packaging. High temperatures and humidity may reduce shelf life.

HEALTH & SAFETY

Congrout Admix is non-hazardous, but work cleanly and wear protective clothing. In windy conditions wear a filter mask to avoid inhaling dust. Remove splashes from skin with water and in case of eye contact wash copiously with water.

TECHNICAL SERVICE

The Cormix International Technical Service Department is available to assist you in the correct use of our products and its resources are at your disposal entirely without obligation.

QUALITY ASSURANCE

ISO 9001 : 2008 verified by TUV Nord.

CONTACT DETAILS

Cormix International Limited

Regional Office,

89 Romklat Rd., Sansab, Minburi, Bangkok 10510

Tel. (66 2) 917 3955-8, 543 8890

Fax. (66 2) 917 3959, 543 8891

<http://www.cormix.com> E-mail : info@cormix.com

NOTE : Every reasonable precaution is taken in the manufacture of all CORMIX-products to ensure that they comply with CORMIX's high standard of quality. The recommendations and properties of the product are based upon what is believed to be the most reliable information available, and are not intended as recommendations which infringe on other patents. Although all CORMIX-products are subject to rigid quality tests, no specific guarantee can be given, because results depend, not only on quality, but also on other factors beyond our control. We welcome therefore consultation in the event of doubt concerning application, or performance, and point out that oral recommendations, which vary from the instructions contained herein, are not binding without written confirmation by CORMIX. All transactions shall be subject to our terms and conditions of sale-delivery-and-service. This data sheet supercedes the previous one and a reprint may be issued without notice to supercede this edition, as and when deemed necessary. The information given in this leaflet is to the best of our knowledge true and reliable. Field service where provided does not constitute supervisory responsibility. Our guarantee is therefore limited to the quality of materials delivered.