

CEMENTITIOUS CARTRIDGE FOR ROCK BOLTING

DESCRIPTION

Congrout Rokfix is a cementitious rock bolting grout packed in a water permeable membrane, forming a shrinkage compensated grout providing high early compressive strengths and fast setting times.

USES & ADVANTAGES

Congrout Rokfix is used for grouting rockbolts as reinforcement in tunneling and mining to protect overhead collapse.

Advantages include:-

- Laboratory tested pre-packed materials.
- Ready to use just add water.
- Non shrink.
- Good adhesion.
- Chloride Free.
- Minimizes grout loss from overhead holes or under conditions of running water.

PROPERTIES

Appearance : Grey powder
Pre soak time with water : At least 1 minute
Yield : Approx. 1 kg = 0.85-0.875 L
Compressive Strength: ≥ 15 MPa at 3 hrs
(at 30°C, Water/Powder ratio : 0.28) ≥ 50 MPa at 28 days
The following table indicates the recommended resistance in tension loading for various sizes of rebar as per ASTM D4435

Rebar Size (mm)	Diameter of Drill Hole (mm)	Depth of Drill Hole (mm)	Recommended Resistance in Tension Loading (kN)
DB12	45	300	28.1
DB16	45	300	50.0
DB20	45	300	78.1

Note: Properties are typical under laboratory conditions and do not constitute a specification. Field trials are recommended.

APPLICATION

- 1) Drill hole to the required length and diameter using drilling machine.
- 2) Remove / clean any dirt / objects from inside the hole.
- 3) Remove **Congrout Rokfix** from plastic and immerse in water at least 1 minute or up to the point where no signs of air release.

- 4) Insert **Congrout Rokfix** one by one into the drilled hole by pushing it using a rod or any long instrument to push it to the bottom of the hole until hole is filled.

Note: Congrout Rokfix sets rapidly, work fast without delay.

PACKAGING

20 cartridges per box.
Packed in a water permeable membrane and protected by a polyethylene cover.

Cartridge nominal diameter : 35 mm. (standard), other diameters on request

Cartridge nominal length : 300 mm. (standard), other lengths on request

STORAGE CONDITIONS & SHELF LIFE

Store in dry shaded conditions. The unused **Congrout Rokfix** to be kept under double line polyethylene cover to avoid exposure to atmosphere. The shelf life is 6 months from date of manufacture in unopened original packaging. High temperatures and humidity may reduce shelf life.

HEALTH & SAFETY

Congrout Rokfix is alkaline avoid contact with skin & eyes. Gloves, goggles and dust mask should be worn. If **Congrout Rokfix** gets into eyes, washed out with copious amounts of clean water and medical attention sought. **Congrout Rokfix** is non-flammable.

TECHNICAL SERVICE

The Cormix International Technical Service Department is available to assist you in the correct use of our products and its resources are at your disposal entirely without obligation.

QUALITY ASSURANCE

ISO 9001 : 2008 verified by TUV Nord.

CONTACT DETAILS

Cormix International Limited

Regional Office,
89 Romklat Rd., Sansab, Minburi, Bangkok 10510
Tel. (66 2) 917 3955-8, 543 8890
Fax. (66 2) 917 3959, 543 8891
<http://www.cormix.com> E-mail : info@cormix.com

Rev. 005 : Nov 2014

NOTE : Every reasonable precaution is taken in the manufacture of all CORMIX-products to ensure that they comply with CORMIX's high standard of quality. The recommendations and properties of the product are based upon what is believed to be the most reliable information available, and are not intended as recommendations which infringe on other patents. Although all CORMIX-products are subject to rigid quality tests, no specific guarantee can be given, because results depend, not only on quality, but also on other factors beyond our control. We welcome therefore consultation in the event of doubt concerning application, or performance, and point out that oral recommendations, which vary from the instructions contained herein, are not binding without written confirmation by CORMIX. All transactions shall be subject to our terms and conditions of sale-delivery-and-service. This data sheet supersedes the previous one and a reprint may be issued without notice to supersede this edition, as and when deemed necessary. The information given in this leaflet is to the best of our knowledge true and reliable. Field service where provided does not constitute supervisory responsibility. Our guarantee is therefore limited to the quality of materials delivered.