

ALKALI-FREE LIQUID HARDENING ACCELERATOR

DESCRIPTION

Conmix AFL is an alkali-free liquid admixture formulated to provide hardening acceleration in shotcrete, while reducing the safety hazards associated with traditional alkaline shotcrete accelerators. It may be used for shotcrete applied by dry or wet spraying. Complies of ASTM C1141, Type II & Grade 9, Class A.

USES & ADVANTAGES

Conmix AFL can be used with shotcrete in tunneling, mining, and slope stabilisation. It is ideally suited for wet mix sprayed concrete for rock support due to:

- The quick setting properties which allow for rapid work progress and the ability to construct thick sprayed concrete linings via layered application during construction sequence.
- The product formulation which provides continual early-age strength development whilst also achieving excellent long-term strength and durability.
- **Conmix AFL** being a liquid product provides easy handling, as well as facilitating accurate addition to the concrete.
- Very low dust production and therefore a good working environment. Product is also non aggressive, it provides improved working safety and environmental impact.

Advantages include:

- Quick setting.
- Early-age strength development, excellent long-term strength and durability.
- High resistance to carbonation.
- Reducing water permeability.
- Very low dust production.
- Improves safety and non-toxic.
- Better adhesion.
- Reduced rebound.
- Alkali free.

PROPERTIES

Appearance:	Clear Liquid
pH Value (5% solution):	Approx. 1.85-2.85
Density:	Approx. 1.30-1.36 kg/ltr.
Na₂O:	<0.1%
Chloride Content (Cl⁻):	<0.01%

**Properties are typical under laboratory conditions and do not constitute a specification. Field trials are recommended.*

APPLICATION

According to the required setting time and early strengths, **Conmix AFL** can be added at a dosage of 3-10% by weight of binder. Overdosing may result in decreased strength.

The dosage depends on temperatures, reactivity of cement used, required thickness of layers, setting time and early strength development required. We recommend the use of fresh cement.

Dosage equipment and pumps must be made of acid-resistant materials.

Mono pumps (screw pumps) and squeeze pumps (rotary pumps) can work well, but piston pumps, pressure tanks and gear pumps should not be used.

It is preferable to use concrete with cement contents of no less than 400 kg/m³ for high early strength.

Conmix AFL can be sensitive to different types of cement. It is suggested to use 100% clinker Portland cement for earlier setting time.

During wet-mix spraying, the w/c ratio should be below 0.5 (preferably below 0.45) to achieve better results. The water content in aggregate must be taken into account in the calculation of water-cement ratio.

Conmix AFL is added at the nozzle through a separate accelerator hose.

To facilitate dosage it is recommended to agitate **Conmix AFL** before hand, as the material is self-thickening, or rather has a tendency to sedimentation after long term storage.

Before **Conmix AFL** is used, the entire dosing equipment must be thoroughly cleaned with a lot of water. During concreting and work breaks the system must remain closed to avoid blockage.

Conmix AFL must not be stored in steel containers. The storage containers must be closed tightly to avoid the evaporation of the water and resulting film formation on the surface.

Prior to and after using **Conmix AFL**, clean the hoses, pumps, and other instruments thoroughly with plenty of water.

Do not mix Conmix AFL with any type of accelerator produced by another manufacturer, as this could cause immediate clogging of pumps and hoses.

All necessary suitability tests must be performed before use.

GENERAL INFORMATION - SHOTCRETE MIX DESIGN

Typical Shotcrete Mix Design

Ordinary Portland Cement Type I	420 kg/m ³
River Sand	700 kg/m ³
Crushed Rock Fines	500 kg/m ³
Aggregates <10 mm	450 kg/m ³
Water	189 litre/m ³

The above is a typical shotcrete mix design excluding superplasticisers, silica fume, steel fibres, accelerators and other additives.

Gradation Limits for Shotcrete Aggregate

Sieve Sizes (mm)	% by Weight Passing Individual Sieves		
	Gradation No.1	No.2	No.3
19	-	-	100
12.5	-	100	80-95
9.5	100	90-100	70-90
4.75	95-100	70-85	50-70
2.36	80-100	50-70	35-55
1.18	50-85	35-55	20-40
0.60	25-60	20-35	10-30
0.30	10-30	8-20	5-17
0.15	2-10	2-10	2-10

ALKALI-FREE LIQUID HARDENING ACCELERATOR

Dry Mix

Dry mix shotcrete must allow for increased rebound composed mainly of larger aggregate, unlike wet mixes increase aggregate contents to allow for loss in application is not a problem. Below is a typical dry mix shotcrete mix design. In dry mix shotcrete usually the only type of admixtures used are accelerators combined with silica fume and steel fibres.

Sample Dry Mix (Design 1 m³):

Aggregate (Gradation No.2)	1,670 kg
Cement	350-400 kg
Silica Fume (Conmix SF1)	50 kg
Steel Fibres (if required)	40-60 kg

Wet Mix

Wet mix design is similar to pumpable concrete mixes. The material must be flowable enough at low water cement ratios to flow through the hose stay in place once blown onto the surface and rapidly gain strength.

Wet mix shotcrete typically contains Superplasticisers (**Conmix SP1**), Retarders (**Conmix R1**), Air Entrainers (**Conair**), Silica Fume (**Conmix SF1**) and Steel Fibres.

Below is a typical wet mix shotcrete design:

Sample Wet Mix (Design 1 m ³)	
Aggregate (Gradation No.2)	1,600 kg
Cement	420 kg
Silica Fume (Conmix SF1)	40 kg
Superplasticiser, Water Reducer (Conmix SP1, Conmix R1)	
& Air Entrainer (Conair)	5-10 kg
Water (approx.)	210 kg
Steel Fibres (if required)	40-60 kg

Cormix International technical service department is available to advise on shotcrete mix design and the appropriate additives to use.

Dry & Wet Shotcrete Additives Available from Cormix

Dry Mix Additives

Conmix AFP	Alkali Free Powder Accelerator
Conmix GA2	Standard Powder Accelerator
Conmix SF1	Silica Fume
Conmix Steel Fibres	

Wet Mix Additives

Conmix GA1	Standard Liquid Accelerator
Conmix AFL	Alkali Free Liquid Accelerator
Conmix SP1	Superplasticiser Admixture
Conmix R1/P4	Retarding & Plasticising Admixture
Conmix SF1	Silica Fume
Conair	Air entraining Additive
Conmix Steel Fibres	

PACKAGING

Conmix AFL is supplied in 200 litre drums or 1,000 litre IBC tanks.

STORAGE & SHELF LIFE

Conmix AFL must be stored at a minimum of +5°C and maximum of +35°C. **Conmix AFL** has to be kept in closed containers made of plastic, glass fibre plastic or stainless steel. **Conmix AFL** must not be stored in normal steel containers as the pH can cause corrosion that may affect the performance of the product.

After prolonged storage we recommend that **Conmix AFL** always be fully agitated prior to use by mechanical stirring or re-circulation pumping. Agitation by compressed air is strictly not advised.

If stored in tightly closed original containers under the above given conditions, **Conmix AFL** has a shelf life of 3-6 months.

Open containers will allow prolonged contact with air leading to skin film and lumps being produced that may cause blocking of accelerator system.

It is recommended that your local Cormix International representative be consulted prior to the use of any product that has been frozen.

Performance testing should always be carried out before use.

HEALTH & SAFETY

Wear rubber gloves and goggles to avoid eye and skin contact. If contact occurs, clean with plenty of water. In case of eye contact, seek medical advice.

TECHNICAL SERVICE

The Cormix International Technical Service Department is available to assist you in the correct use of our products and its resources are at your disposal entirely without obligation.

QUALITY ASSURANCE

ISO 9001 : 2008 verified by TUV Nord.

CONTACT DETAILS

Cormix International Limited

Regional Office

89 Romkloa Rd., Sansab, Minburi, Bangkok 10510

Tel. (66 2) 917 3955-8, 543 8890

Fax. (66 2) 917 3959, 543 8891

<http://www.cormix.com> E-mail : info@cormix.com

NOTE : Every reasonable precaution is taken in the manufacture of all CORMIX-products to ensure that they comply with CORMIX's high standard of quality. The recommendations and properties of the product are based upon what is believed to be the most reliable information available, and are not intended as recommendations which infringe on other patents. Although all CORMIX-products are subject to rigid quality tests, no specific guarantee can be given, because results depend, not only on quality, but also on other factors beyond our control. We welcome therefore consultation in the event of doubt concerning application, or performance, and point out that oral recommendations, which vary from the instructions contained herein, are not binding without written confirmation by CORMIX. All transactions shall be subject to our terms and conditions of sale-delivery-and-service. This data sheet supersedes the previous one and a reprint may be issued without notice to supersede this edition, as and when deemed necessary. The information given in this leaflet is to the best of our knowledge true and reliable. Field service where provided does not constitute supervisory responsibility. Our guarantee is therefore limited to the quality of materials delivered.