

LIQUID ADMIXTURE FOR IMPROVING SHOTCRETE

DESCRIPTION

Conmix TLA is an admixture for use in shotcrete applications to improve shotcrete both in its hardened & plastic state.

USES & ADVANTAGES

Conmix TLA is used where a high quality shotcrete is required with better bond, and lower permeability.

Advantages include:-

- Better cement hydration.
- Reduced permeability.
- Improved workability.
- Non toxic, water based, nonflammable.
- Reduced shrinkage.
- Increased strengths.
- Improved pumpability.
- Better bond.

PROPERTIES

Form:	Liquid
Specific Gravity:	Approx. 1.022
pH Value:	Approx. 9.13
Colour:	Milky white
Viscosity:	6.63 mPa.s

Properties are as found in the laboratory & are for guidance only.

Compatibility with Cements:

Conmix TLA is compatible with all types of cements, silica fume & pozzolanic materials. It may be used with most types of admixtures. Consult **Cormix** for advice.

MIXING

The product is ready to use and is added to the mix with the last 25% of the mix water. It may be dosed through standard dispensers.

DOSAGE

The standard dosage is 5 kg/m³ of shotcrete, however, the dosage may be varied depending on conditions and the required results.

Trial mixes are always recommended in advance of starting work.

PACKAGING

Conmix TLA is supplied in 25 & 200 litre drums.

STORAGE & SHELF LIFE

Store in shaded conditions in a dry warehouse in unopened containers at temperatures of +5°C to +50°C. If stored in the right conditions the product has a shelf life of at least 6 months. Failure to store correctly may result in the product deterioration.

HEALTH & SAFETY

Wear suitable protective clothing, gloves and eye protection. The use of barrier creams provide additional skin protection. In case of contact with skin, rinse with plenty of clean water, then cleanse with soap and water. If poisoning occurs, contact a doctor or Poisons Information Centre. If swallowed, **DO NOT** induce vomiting - give a glass of water. If in eyes, hold eyes open, flush with water for at least 15 minutes and see a doctor. If skin contact occurs, remove contaminated clothing and wash skin thoroughly with soap and water.

TECHNICAL SERVICE

The Cormix International Technical Service Department is available to assist you in the correct use of our products and its resources are at your disposal entirely without obligation.

QUALITY ASSURANCE

ISO 9001 : 2008 verified by TUV Nord.

CONTACT DETAILS

Cormix International Limited

Regional Office,
89 Romklao Rd., Sansab, Minburi, Bangkok 10510
Tel. (66 2) 917 3955-8, 543 8890
Fax. (66 2) 917 3959, 543 8891
<http://www.cormix.com> E-mail : info@cormix.com

Rev. 002 : Jun 2010

NOTE : Every reasonable precaution is taken in the manufacture of all CORMIX-products to ensure that they comply with CORMIX's high standard of quality. The recommendations and properties of the product are based upon what is believed to be the most reliable information available, and are not intended as recommendations which infringe on other patents. Although all CORMIX-products are subject to rigid quality tests, no specific guarantee can be given, because results depend, not only on quality, but also on other factors beyond our control. We welcome therefore consultation in the event of doubt concerning application, or performance, and point out that oral recommendations, which vary from the instructions contained herein, are not binding without written confirmation by CORMIX. All transactions shall be subject to our terms and conditions of sale-delivery-and-service. This data sheet supersedes the previous one and a reprint may be issued without notice to supersede this edition, as and when deemed necessary. The information given in this leaflet is to the best of our knowledge true and reliable. Field service where provided does not constitute supervisory responsibility. Our guarantee is therefore limited to the quality of materials delivered.